

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
26 April 2001 (26.04.2001)

PCT

(10) International Publication Number
WO 01/29271 A1

(51) International Patent Classification⁷: C21C 5/52, 5/54

(21) International Application Number: PCT/NO00/00345

(22) International Filing Date: 18 October 2000 (18.10.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
19995072 18 October 1999 (18.10.1999) NO

(71) Applicant (for all designated States except US): NORSK
HYDRO ASA [NO/NO]; N-0240 Oslo (NO).

(72) Inventors; and

(75) Inventors/Applicants (for US only): TUVNES, Petter
[NO/NO]; Olav Trygvasson v 10, N-3960 Stathelle (NO).
ENGH, Thorvald, Abel [NO/NO]; Øvre Selsbakk 38,
N-7027 Trondheim (NO).

(74) Agent: ANDERSON, Elin; Norsk Hydro ASA, N-0240
Oslo (NO).

(81) Designated States (national): AE, AL, AM, AT, AU, AZ,
BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK,
DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL,
IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU,
LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT,
RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA,
UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG,
CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

- With international search report.
- Before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments.

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: METHOD AND USE OF CALCIUM NITRATE FOR FOAMING OF STEEL-MAKING SLAGS

(57) Abstract: The invention concerns a method of foaming steel-making slags, wherein calcium nitrate is added to the slag alone or together with carbon. Calcium nitrate and carbon can be fed into the slag trough chutes or trough lances with injection gases such as air, nitrogen, carbon dioxide or inert gases. The solid components can be injected separately or with the same lance as a mixture or injected as pre-fused granules. For ladle slag foaming, calcium nitrate and carbon is added from above the melt. It is preferred to use a ratio between calcium nitrate and carbon in the range from 4.1 to 2:1. For foaming of stainless steel slag, it is preferred to add FeSi, Al or Mg before calcium nitrate and carbon is added or injected into the slag by an injection gas. Air, nitrogen, carbon dioxide or inert gases can be used as injection gas. The invention also concerns the use of calcium nitrate as a foaming agent for steel-makings slags. The invention can be used for slag foaming in electric arc furnaces and ladles.

WO 01/29271 A1